

# Declaration of Conformity

**Of product: 910417 (111/00711)**

1.	Name and address of the manufacturer:	"Umaras" , UAB, Pramonės str. 19a, Utena, Lithuania LT - 28216			
2.	Raw materials and additives used in production	Polyethylene Opening additive Slipperiness additive Anti-static additive Additive of the manufacturing process			
3.	Date of the submission of the declaration	07/06/2023			
4.	Confirmation that the packaging is in conformity	<p>* With the relevant requirements set out in Article 3 of Regulation (EC) No. 1935/2004 under intended and foreseeable use;</p> <p>*With the relevant requirements set out in Part 5 of Regulation (EC) No. 1935/2004 11;</p> <p>* With the labelling requirements set out in Article 15 of Regulation (EC) No. 1935/2004;</p> <p>* With the traceability requirements set out in Article 17 of Regulation (EC) No. 1935/2004;</p> <p>*The products are manufactured in compliance with the good manufacturing practice as set out in the Commission Regulation (EC) No. 2023/2006;</p> <p>*Conforms to the relevant requirements of composition and declaration set out in Articles II, III and IV of the Regulation (EC) No. 10/2011.</p> <p>*The materials used comply with the requirements set out in the Regulation (EC) No. 1935/2004 and the risk assessment was carried out in accordance with Article 19 of the Regulation (EC) No. 10/2011.</p> <p>*Regulation (EU) 2020/1245 amending Regulation (EU) No 10/2011: on plastic materials and articles intended to come into contact with food. (<i>Deadline for this compliance was 23.09.2022</i>)</p>			
5.	Materials and additives with limit values of emissions.	Chemical name:	Cas. No.	REF. No.	SML
		1-octene	0000111-66-0	22660	15mg/kg
		Stearic acid	00057-11-4	24550	-
		Lubricant	00057-11-4	89040	-
		Tris(2,4-di-tret-butylfenil)ester	0031570-04-4	74240	-
		Erucamide	0000112-84-5	52720	-
		Oktadecil 3-(3-(3,5-di-tret-butyl-4-hidroksifenil)propionate	0002082-79-3	68320	6mg/kg

6.	Dual-purpose additives	Chemical name:	Cas. No.	REF. No.		
		Carbonic acid salts	-	42500		
7.	Use of film	The film can be used for contact with all food types.				
8.	Time and temperature when in contact with foods.	Any food stored for long periods at room temperature or below (frozen, refrigerated), including heating to 70°C for up to 2 hours or to 100°C for up to 15 minutes.				
9.	General migration in the product.	The analysis of general migration was carried out in accordance with regulation (EC) 10/2011. This analysis confirms that the results of general migration, specified below, do not exceed the limits (10mg/dm <sup>2</sup> ) of the allowed general migration set out in regulation (EC) specified above. The value of migration shall be expressed in mg/kg applying a surface to volume ratio of 6 dm2 per kg of food. The packaging conforms to the organoleptic requirements. Bisphenol A is not used in manufacturing and during the process of manufacturing.				
		Analyte	Mark of method	Result	Conditions of the analysis	Measuring unit
		Overall migration into 3% acetic acid	LST EN 1186-3:2002	< 0,5	10 days at 40 °C	mg/dm <sup>2</sup>
		Overall migration into ethanol	LST EN 1186-3:2002	< 0,5	10 days at 40 °C	mg/dm <sup>2</sup>
		Overall migration into ethanol 95%	LST EN 1186-14:2002, except 4,5 p.	< 0,8	10 days at 40 °C	mg/dm <sup>2</sup>
		Overall migration into isooctane	LST EN 1186-14:2002, except 4,5 p.	< 1,7	2 day at 20 °C	mg/dm <sup>2</sup>
		Explanations: Acetic acid 3% - food simulant B; Ethanol - food simulant A, ethanol 10 %; Ethanol 95% - substitute food simulant D2; Isooctane - substitute food simulant D2;  Protocol of the chemical analysis: Ch7217/2022				
10.	Functional barrier	Here is no functional barrier in the film.				
11.	Conditions for storage	It is recommended to store the film in covered rooms that are not exposed to direct UV, at a temperature of +15 to +35 °C, at a relative humidity of less than 85% and at a distance of at least 1 m from heating devices. Before use, the film must be kept at working temperature for at least 24 hours. If the film is transported or stored at a temperature below +15 °C or above +35 °C, it is recommended to store it at working temperature for at least 48 hours before further use.				



FLEXIBLE PACKAGING

		If the film is transported or stored at a temperature below +5 °C or above +40 °C, it is recommended to store it at working temperature for at least 72 hours before further use.
--	--	---

The declaration of conformity is valid for one year from the date it was signed.

Approved by: Quality specialist, S.Gančiauskienė